



GARAPA

Apuleia Leiocarpa



PREMIUM ARCHITECTURAL
& BUILDING SOLUTIONS

JSC Premium Garapa, the right choice for all budgets



Class 2 durability



Slip and scratch
resistant



Premium grade

Garapa is sourced from the tropical forests of South America. Garapa timber, also known as Brazilian Ash, is dense and naturally durable.

Garapa is a fine quality exotic hardwood, and is naturally resistant to rot, decay and insect attack.

Its consistent golden colour and straight grain make it a useful alternative to more common hardwoods. The attractive light colour makes it especially suitable for decks exposed to long hours of direct sun as it is cooler underfoot.



GARAPA APPLICATIONS

JSC Premium Garapa is naturally slip and scratch resistant which allows the surface to remain smooth for many years, making Garapa a perfect wood for exterior decking. Premium Garapa machines to a fine finish with little tendency to splinter or move.

- **Sustainable** - JSC Premium Garapa is FSC® and sourced from sustainably harvested forests in South America.
- **Naturally durable** - An exotic tropical hardwood that is naturally resistance to rot, decay, and insect attack. Garapa has a naturally scratch- resistant surface allowing a smooth surface for years to come
- **Premium Grade** - JSC stocks Premium Grade Garapa with fewer defects and long length spreads to make installing quicker and easier, with less time and docking waste.



TECHNICAL INFORMATION

Working qualities	Easy to work with
Supplier responsibility status	FSC
Availability of sizes	Lengths: Random lengths only ranging from 1.8m - 4.8m and longer in some cases Width: 90mm & 140mm wide Thickness: 19mm
Durability	Class 2*
Grades	Select and Better

*Durability classifications provide a useful comparative guide, however factors relating to specific installations and natural timber variation may result in heartwood pieces falling outside the species' durability classification.

Mechanical properties	Dry
Modulus of Rupture (MPa)	128
Modulus of Elasticity (GPa)	15.6
Hardness Janka (kN)	7.3
*Density (kg/m3) *Air dry density (kg/m3) is average indication only and actual value may vary.	*900kg/m ³

Note: For comparable species speak to the JSC team about alternatives.

Disclaimer: JSC has endeavored to ensure this information is accurate but recommends for critical applications that independent advice is obtained. These properties are a guide only, as timber is a natural product there will be variations within any species. Please speak to our professionals at JSC for information and advice as well as for any information around profiles, fixing details and supporting documentation.

jsc.co.nz

TechHelp@jsc.co.nz

Sales@jsc.co.nz

FIND JSC ONLINE  

AUCKLAND

(09) 412 2800
22 Sawmill Road
Riverhead

HAMILTON

0800 57 26 88
43 McKee Street
Pukete

WELLINGTON

0800 57 26 88
61 Seaview Road
Seaview

CHRISTCHURCH

(03) 348 9726
72 Hammersmith Drive
Sockburn

 **JSC** PREMIUM ARCHITECTURAL
& BUILDING SOLUTIONS