

SAMBARA

Triplochiton scleroxylon



PREMIUM ARCHITECTURAL
& BUILDING SOLUTIONS

A perfect choice for interior applications



Ideal for detailed
interior profiles



Lightweight



Light colour that
stains very well

Sambara (African whitewood) is a lightweight West African hardwood commonly selected for interior joinery and lining where a consistent, light coloured warm appearance is desired. It machines easily and takes paint, stain, and clear finishes well, making it a versatile choice for interior panelling, ceilings, battens, mouldings, and general fit-out work.

Typically cream to straw in colour with little distinction between sapwood and heartwood, Sambara has a medium texture with natural grain variation that may present as subtle figuring or ribboning.



Sambara coated in JSC Coda Lux Wax (White, Brown, & Black)

SAMBARA APPLICATIONS

Sambara works well with hand and machine tools and is suited to interior applications such as:

- Interior joinery
- Interior wall panelling & ceilings
- Feature battens
- Compatible with the JSC Clipp Batten System
- Mouldings / trims

TECHNICAL INFORMATION

Supplier responsibility status	Certified Timber
Availability of sizes	Lengths: 1.8m – 4.8m Thickness: Commonly available in 25mm & 50mm Width: 100mm, 150mm, & 200mm
Durability	Class 4* - For interior use only
Grades	Clears

*Durability classifications provide a useful comparative guide, however factors relating to specific installations and natural timber variation may result in heartwood pieces falling outside the species' durability classification.

Mechanical properties	Green	Dry
Modulus of Rupture (MPa)	37 MPa	55–61 MPa
Modulus of Elasticity (GPa)	4.55 GPa	5.52–6.48 GPa
Hardness Janka (kN)	1.87 kN	1.91 kN
*Density (kg/m ³) *Air dry density (kg/m ³) is average indication only and actual value may vary.	-	*380 kg/m ³

Note: For comparable species speak to the JSC team about alternatives.

Disclaimer: The timber properties and product information provided in this document are intended as general guidelines only. Actual timber characteristics may vary due to origin, growth conditions, environmental influences, and natural variation. JSC has not conducted specific testing on the timber properties referenced; all figures are indicative only and have been sourced from external references cited within this document. Information relating to JSC products is necessarily general in nature and subject to variation in dimension, appearance, and specification, depending on natural factors, installation methods, or the specific application. Customers must independently verify all technical data and obtain professional advice to determine the suitability of any product for their particular purpose. The Customer is solely responsible for ensuring that the product is appropriate for its intended use. JSC does not accept any liability (including for negligence) for claims arising from reliance on this information, documentation, or other related materials.

jsc.co.nz

TechHelp@jsc.co.nz

Sales@jsc.co.nz

FIND JSC ONLINE



AUCKLAND

(09) 412 2800
22 Sawmill Road
Riverhead

HAMILTON

0800 57 26 88
43 McKee Street
Pukete

WELLINGTON

0800 57 26 88
61 Seaview Road
Seaview

CHRISTCHURCH

(03) 348 9726
23 William Lewis Drive
Sockburn



PREMIUM ARCHITECTURAL
& BUILDING SOLUTIONS